## Deckdrain 1200S/NW8



DECKDRAIN 1200S/NW8 is a geocomposite drainage layer comprising a high performance single cuspated HDPE (High Density Polyethylene) core with a geotextile filter thermally bonded to one side. The textile filter has a flap that extends beyond the core on one edge. The product is practically impermeable one side. It is used as an engineered drainage layer in structural applications, its major areas of use being behind retaining structures, on roof decks and in subsurface works.

Geocomposite Properties								
Thickness at 2kPa	(mm)	12.0			±10%	EN ISO 9863-1		
Mass per unit area	$(g/m^2)$	1070			approx	EN ISO 9864		
Tensile strength MD / CMD	(kN/m)	9.5 / 9.5			-13%	EN ISO 10319		
Elongation at peak MD / CMD	(%)	40 / 50			nominal	EN ISO 10319		
CBR puncture resistance	(N)	2 300			-20%	EN ISO 12236		
Perpendicular Water Inflow	(dimple	(dimple side only)						
Water flow at 50mm head	(I/m²·s)	98			±30%	EN ISO 11058		
At 2kPa permeability (coefficient)	(m/s)	2.6 x 10 <sup>-3</sup>			±30%	EN ISO 11058		
Breakthrough head	(mm)	0			nominal			
In-plane water flow MD <sup>2</sup>		<u>HG = 1.0</u>		<u>HG = 0.1</u>		Hydraulic gradient		
at 20kPa confining pressure	(l/m·s)	4.25	-20%	1.25	-20%	EN ISO 12958		
at 100kPa confining pressure	(l/m·s)	3.30	-25%	0.90	-25%	EN ISO 12958		
at 200kPa confining pressure	(l/m·s)	2.80	-35%	0.80	-35%	EN ISO 12958		
with ask faces contact surface on the dimple side to simulate toutile intrusion into the care due to sail procesure and hand								

with **soft foam** contact surface on the dimple side to simulate textile intrusion into the core due to soil pressure and **hard** contact surface on the flat side to simulate installation on rigid surfaces. The confining pressures of the flow rates shown above are all equal to or less than the long-term compressive strength of the product.

Positore to weathering.

To be sovered in 28 days.

Resistance to weathering		To be covered in 28 days		EN 12224			
Resistance to chemicals		Excellent		EN 14030			
Design life		120 years (manufacturer's declaration)					
<b>Geotextile Properties</b>							
Thickness at 2kPa	(mm)	1.2	±20%	EN ISO 9863-1			
Tensile strength MD/CMD	(kN/m)	9.5 / 9.5	-13%	EN ISO 10319			
Pore size 0 <sub>90</sub>	(µm)	120	±30%	EN ISO 12956			
CBR puncture resistance	(N)	1 600	-20%	EN ISO 12236			
Dynamic perforation cone drop	(mm)	32	+20%	EN ISO 13433			
Type and material	Non-wo	Non-woven needle-punched and heat-treated long staple fibre polypropylene					
<b>Product Dimensions</b>							
Standard roll dimensions	1.1 m x	1.1 m x 50 m or 2.2 m x 25 m. Other sizes on request.					

- 1. The values given are indicative and correspond to nominal results obtained in our laboratories and testing institutes. In line with our policy of continuous improvement the right is reserved to make changes without notice at any time.
- 2. Final determination of the suitability of any information is the sole responsibility of the user. ABG would be pleased to discuss the use of this or any other product but responsibility for selection of a material and its application in any specific project remains with the user.
- 3. The tolerance on roll length is ±1.5% and on roll width is ±1.0%; in multi-core products this may manifest itself between core elements.
- 4. Guidance on interface shear strength, creep and certain other parameters is available. Site specific tests are strongly recommended.

